

REPORT ON THERMAL CONDUCTIVITY OF CONCRETE

Page 1 of 1

ACES Client	ESPAC -Precast Aerated Concrete	Report No.	KMR16000659
Sample No.	KMS16000182	Date Reported	16-04-16
Request No.	KMQ16000141	Sample No.	KMS16000182
Project Name	Autoclaved Aerated Concrete Products testing		
Structural Reference	-	Sampling Method	Sample Description
Sample Description	Autoclaved Aerated Concrete Proucts	Sample Brt. In By	Client's Rep.
Test Method	ASTM C177	Date Tested	17-03-16
Method Variation	-	Tested By	Wassel

Sr. No.	Thermal Conductivity	Density (g/cm3)
1	0.11 W/mK	0.57



Rashad A. Al Kilani
Branch Manager
Arab Company for Laboratories & Soil (ACES)

